

CCEFIRE® DJM Series Insulating Fire Brick

Description:

CCEFIRE® DJM series Mullite insulation brick is a new type of refractory material, which can directly contact with fire, characterized with high temperature resistance, lightweight, low thermal conductivity, good energy saving effect, specially suitable for cracking furnace, hot blast furnace, ceramic roller kiln, porcelain kiln extraction, glass crucible and various electric furnaces as lining. It is an ideal product of energy efficiency and longevity.

Technical data and Size:

CCEFIRE® DJM series mullite insulating brick								
Item	DJM20	DJM-23	DJM-24	DJM-26	DJM-28	DJM-30	DJM-32	
Classification Temp(°C)	1200	1260	1300	1430	1540	1650	1760	
Bulk Density(g/cm3)	0.5	0.6	0.7	0.8	0.9	1	1.25	
Crushing Strength(MPa)	1.1	1.2	1.4	1.6	2.1	2.5	3.5	
Modulus of Rupture(MPa)	1.0	0.9	1.2	1.4	1.6	2.1	2.1	
Permanent linear change (CT-30°Cx24h)%	0.5	0.5	0.6	0.4	0.5	0.9	0.9	
Reversible thermal expansion at 1100°C	0.5	0.5	0.6	0.7	0.8	0.9	1.1	
Thermal	400 °C	0.12	0.12	0.14	0.27	0.32	0.41	0.49

Zibo Double Egret Thermal Insulation Co.,Ltd

Add: No.105 Liuquan Rd Zibo Shandong

Tel: +86-533-7986860

Fax: +86-533-6077229

Email: ceramicfibres@ccewool.com

Website: www.ceramicfibres.com

www.cceramicfiber.com

www.cerockwool.com

conductivity (W/m.k)	600 °C	0.14	0.14	0.16	0.29	0.34	0.43	0.5
	800 °C	0.16	0.17	0.18	0.31	0.36	0.44	0.51
	1000 °C	0.18	0.19	0.2	0.33	0.38	0.45	0.53
	1200 °C	-	-	-	0.3	0.41	0.47	0.56
Chemical Analysis(%)	Al₂O₃	37	37	44.5	58	67	73	77
	SiO₂	47	44.4	41.2	39.1	31	25.1	21.5
	Fe₂O₃	0.7	0.7	0.7	0.7	0.6	0.5	0.4
Common size of insulation brick	230x114x65/75mm or customized size							

Raw Materials

Own large-scale ore base, professional mining equipment, and stricter selection of raw materials.

The incoming raw materials are tested first, and then the qualified raw materials are kept in a designated raw material warehouse to ensure their purity.

The raw materials of CCEFIRE insulation bricks have low impurity content with less than 1% oxides, such as iron and alkali metals. Therefore, CCEFIRE insulation bricks have high refractoriness, reaching 1760°C. The high aluminum content makes it maintain good performances in a reducing atmosphere.

Production Process

Zibo Double Egret Thermal Insulation Co.,Ltd

Add: No.105 Liuquan Rd Zibo Shandong

Tel: +86-533-7986860

Fax: +86-533-6077229

Email: ceramicfibres@ccewool.com

Website: www.ceramicfibres.com

www.ceceramicfiber.com

www.cerockwool.com

The fully automated batching system fully guarantees the stability of the raw material composition and better accuracy in raw material ratio.

With internationally advanced automated production lines of high-temp tunnel furnaces, shuttle furnaces, and rotary furnaces, the production processes from raw materials to finished products are under automatic computer-control, ensuring stable product quality.

Automated furnaces under stable temperature control produce CCEFIRE insulation bricks with thermal conductivity lower than 0.16w/m.k in an environment of 1000 °C, and they have excellent thermal insulation performance, less than 05% in the permanent linear change, stable quality, and longer service life.

Insulation bricks of various shapes are available according to designs. They have accurate sizes with the error controlled at +1mm and are convenient for customers to install.

Quality Control

Each shipment has a dedicated quality inspector, and a test report is provided prior to the departure of products from the factory to ensure the export quality of each shipment of CCEFIRE.

A third-party inspection (such as SGS, BV, etc.) is accepted.

Production is strictly in accordance with ASTM quality management system certification.

Zibo Double Egret Thermal Insulation Co.,Ltd

Add: No.105 Liuquan Rd Zibo Shandong

Tel: +86-533-7986860

Fax: +86-533-6077229

Email: ceramicfibres@ccewool.com

Website: www.ceramicfibres.com

www.ceceramicfiber.com

www.cerockwool.com

The outer packaging of each carton is made of five layers of kraft paper, and outer packaging + pallet,, suitable for long-distance transportation.

Application Performance

CCEFIRE insulation bricks have low thermal conductivity and good thermal insulation effects.

CCEFIRE insulation bricks have low thermal melting, and due to their low thermal conductivity, they accumulate very little heat energy, which leads to their remarkable energy-saving effects in intermittent operations.

CCEFIRE thermal insulation bricks have low impurity content, especially very low in iron and alkali metal oxide content, so they have high refractoriness. Their high aluminum content allows them to maintain good performance in a reducing atmosphere.

CCEFIRE mullite insulation bricks have high thermal compressive strengths.

CCEFIRE thermal insulation bricks have accurate dimensions in appearance, which can speed up the construction speed, reduce the amount of refractory clay used, and ensure the strength and stability of the masonry, thereby extending the service life of the lining.

CCEFIRE mullite insulation brick can be processed into special shapes to reduce the number of bricks and joints.

Based on the above advantages, CCEFIRE insulation bricks and fiber ropes are widely used in hot blast furnace top, blast furnaces' body and bottom,

Zibo Double Egret Thermal Insulation Co.,Ltd

Add: No.105 Liuquan Rd Zibo Shandong

Tel: +86-533-7986860

Fax: +86-533-6077229

Email: ceramicfibres@ccewool.com

Website: www.ceramicfibres.com

www.cceramicfiber.com

www.cerockwool.com



Zibo Double Egret Thermal Insulation Co., Ltd.

Insulation · Refractory · Eco-friendly

glass melting furnaces' regenerator, ceramic sintering furnaces, dead corner furnace lining of petroleum cracking system, and the lining of ceramic roller furnaces, electric porcelain drawer furnaces, glass crucible and various electric furnaces.

Zibo Double Egret Thermal Insulation Co.,Ltd

Add: No.105 Liuquan Rd Zibo Shandong

Tel: +86-533-7986860

Fax: +86-533-6077229

Email: ceramicfibres@ccewool.com

Website: www.ceramicfibres.com

www.ceceramicfiber.com

www.cerockwool.com