

CCEWOOL® Rock Wool Blanket **with Wire Mesh**

Description:

CCEWOOL heat-resistance Rock Wool blanket with Wire Mesh is manufactured in rolls, which is made from rock wool felt and galvanized iron wire mesh or stainless-steel wire mesh sewn together with galvanized iron wire or stainless-steel wire. It features good elasticity, thermal preservation, and easy construction. Water repellent type and low chlorine type of products can be manufactured according to the requirement of customers. Aluminum foil, fiberglass cloth, and other veneer materials can also be overlaid to the surface of products.

CCEWOOL heat-resistance Rock Wool blanket with Wire Mesh is ideal for thermal insulation, fire prevention and sound absorption and noise reduction in large pipe networks, large storage tanks and containers, furnaces, and air ducts. It is especially suitable for places with high temperature and vibration or where a high fireproof standard is required.

Technical data and Size:

CCEWOOL® Rock Wool Blanket		
Density	80kg/m ³ (GB/T 5480.3)	100kg/m ³ (GB/T 5480.3)
30-70mm Thickness	Length and width: 5000X600mm (GB/T 5480.3)	

75-100mm Thickness	Length and width: 3000X600mm (GB/T 5480.3)	
Thermal Conductivity*	The values are calculated as the average temperature and are in compliance with the relevant test regulations. (GB/T 10294,GB/T 10296)	
70°C	0.040W/ (m.K)	0.038W/ (m.K)
100°C	0.046W/ (m.K)	0.042W/ (m.K)
150°C	0.055W/ (m.K)	0.048W/ (m.K)
200°C	0.064W/ (m.K)	0.056W/ (m.K)
250°C	0.076W/ (m.K)	0.063W/ (m.K)
300°C	0.080W/ (m.K)	0.070W/ (m.K)
350°C	—	0.077W/ (m.K)
400°C	—	0.085W/ (m.K)
Maximum temperature in use	550°C (GB/T 17430, GB50264)	750°C (GB/T 17430, GB50264)
Recommended temperature* in use	450°C (ASTM C411-05, ASTM C447-03, GB50264)	650°C (ASTM C411-05, ASTM C447-03, GB50264)
Flame spread indicator	0 (ASTM E84-10)	
Flue gas development index	≤25 (ASTM E84-10)	
Combustion performance	(GB 8624, EN13501-1, BS 476 Part4) A1 level	
Mass moisture absorption rate	≤1% (ASTM C1104/1104M)	
Volumetric moisture absorption rate	≤1% (ASTM C1104/1104M)	
Chloride content*	≤10ppm (GB/T 17393, ASTM C871-08)	
Water repellency rate	99.5% (GB/T 10299)	
Fiber diameter	≤6μm (GB/T 5480)	

Raw Materials

Zibo Double Egret Thermal Insulation Co.,Ltd

Add: No.105 Liuquan Rd Zibo Shandong

Tel: +86-533-7986860

Fax: +86-533-6077229

Email: ceramicfibres@ccewool.com

Website: www.ceramicfibres.com

www.ceceramicfiber.com

www.cerockwool.com

Selection of high-quality natural rock made of basalt.

Select high-quality ores with advanced mining equipment to avoid the entry of impurities and ensure the sustainability of rock wool.

Production Process

Completely melt the raw materials under 1500°C.

Melt the raw materials at a high temperature of about 1500°C in the cupola and reduce the content of slag balls to keep the low thermal conductivity at high temperatures.

Using four-roller high speed spinner to produce fibers, greatly reduced shot content.

The fibers formed by a four-roll centrifuge at a high speed have the softening point of 900-1000°C. The special formula and mature production technology greatly reduce the content of slag balls, leading to no change in long-term use at 650°C and the enhancement of resistance to high temperatures.

Quality Control

Each shipment has a dedicated quality inspector, and a test report is provided prior to the departure of products from the factory to ensure the export quality of each shipment of CCEWOOL.

Zibo Double Egret Thermal Insulation Co.,Ltd

Add: No.105 Liuquan Rd Zibo Shandong

Tel: +86-533-7986860

Fax: +86-533-6077229

Email: ceramicfibres@ccewool.com

Website: www.ceramicfibres.com

www.ceceramicfiber.com

www.cerockwool.com

A third-party inspection (such as SGS, BV, etc.) is accepted.

Production is strictly in accordance with ISO9000 quality management system certification.

Products are weighed before packaging to ensure that the actual weight of a single roll is greater than the theoretical weight.

The products are packaged with puncture-resistance shrinkable film by an automatic shrink-packaging machine, suitable for long-distance transportation.

Application Performance

1. More fireproof: Class A1 fireproof insulation material, long-lasting working temperature up to 650°C
2. More environmental: neutral PH value, can be used for planting vegetables and flowers, no corrosion to heat preservation medium, and more environmental
3. No water absorption: water repellency rate as high as 99%
4. High strength: pure basalt rock wool boards with greater strengths
5. No delamination: The cotton yarn adopts a folding process and has better drawing results in experiments.
6. Various sizes with the thickness range from 30-120mm can be produced according to customers' requirements.

Zibo Double Egret Thermal Insulation Co.,Ltd

Add: No.105 Liuquan Rd Zibo Shandong

Tel: +86-533-7986860

Fax: +86-533-6077229

Email: ceramicfibres@ccewool.com

Website: www.ceramicfibres.com

www.ceceramicfiber.com

www.cerockwool.com